

DESCRIPTION			
Total thickness	ASTM F386-02	inch	0.085
	EN 428	mm	2.15
Wearlayer thickness	ASTM F410-02	inch	0.028
	EN 429	mm	0.70
Backing	ASTM 1303-04	-	Type B
Weight	-	lbs/sq.ft.	0.57
	EN 430	g/sq.m	2805
Width	-	feet - inch	6'6"
	EN 426	cm	200
Length	-	feet - inch	82'
	EN 426	m	25
Coverage / roll	-	sq.ft.	538.2
	-	sq.m	50
CLASSIFICATION			
Reference specification	ASTM F1303-04	class	Type I Grade 1
Fire rating	ASTM E648-08	class	Class I
	CAN/ULC S102.2	-	tested in accordance
PERFORMANCES			
Bacteriostatic & fungistatic	-	-	Sanosol®
Surface treatment / maintenance	-	-	Protecsol®
Wear resistance	EN 660.2	mm ³	≤ 2.0
Coefficient of friction	ASTM D2047-04	-	0.83
Static load (250 psi)	ASTM F970-00	inch	-0.002
Dimensional stability	-	-	Excellent
Impact insulation class	ASTM E989-06	-	
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Chemical & stain resistance	ASTM F925-02	-	Excellent Test results available upon request
ENVIRONMENT			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	Floorscore™